

IN THE SPECIFICATION

Please insert the following paragraph at page 11, line 23.

A method of producing a toner of the present invention, which comprises: dissolving or dispersing a toner composition comprising a first binder resin and a second binder resin comprising a modified polyester resin in an organic solvent to prepare a solution or a dispersion; mixing the solution or the dispersion with a compound having an active hydrogen atom in an aqueous medium comprising the particulate resin material to react the modified polyester with the compound to prepare a reactant; removing the organic solvent from the reactant to prepare the toner particles; and washing the toner particles to remove excessive particles of the particulate resin material from a surface thereof.